

PBH99

Feature Technical Specifications

The **Bullard PBH99** blocks 99.19% of particulates and offers an ideal balance with a Thermal Protective Performance (TPP) of 20.4 cal/cm² while maximizing the Total Heat Loss (THL) of 407.5 W/m².

Test & Conditioning	NFPA 1971-2018 Requirement	PBH99
Particulate Blocking Test for each particle size range from 0.1 - 1.0 micron (as received)	≥ 90%	99.19%
Particulate Blocking Test for each particle size range from 0.1 - 1.0 micron after 10 wash/dry, heat conditioning, room conditioning, 10/wash/dry, heat conditioning, room conditioning	≥ 90%	98.77%
Total Heat Loss (THL) As Received	≥ 325 W/m ²	407.5 W/m ²
Thermal Protective Performance (TPP) As Received	≥ 20 cal/cm ²	20.4 cal/cm ²
Thermal Protective Performance (TPP) After 5 Washes	≥ 20 cal/cm ²	30.5 cal/cm ²
Hood Material Burst Strength Interior Layer	≥ 225 N	383N
Hood Material Burst Strength Exterior Layer	≥ 225 N	413N
Seam Breaking Strength	≥ 181 N	794N
INTERIOR LAYER		
Flame Resistance Test 1 - After Flame (as received)	≤ 2 seconds	0 seconds
Flame Resistance Test 1 - After Flame (after 5 washes)	≤ 2 seconds	0.3 seconds
Flame Resistance Test 1 - Char Length (as received) (wales x course)	≤ 100mm	62mm x 84mm
Flame Resistance Test 1 - Char Length (after 5 washes) (wales x course)	≤ 100mm	63mm x 69mm
EXTERIOR LAYER		
Flame Resistance Test 1 - After Flame (as received)	≤ 2 seconds	0 seconds
Flame Resistance Test 1 - After Flame (after 5 washes)	≤ 2 seconds	0 seconds
Flame Resistance Test 1 - Char Length (as received) (wales x course)	≤ 100mm	29mm x 35mm
Flame Resistance Test 1 - Char Length (after 5 washes) (wales x course)	≤ 100mm	42mm x 50mm



How to Measure For Your Size Hood

Distance to measure to determine size. Size corresponds to chart below.


Part Number	Size	Description
PBHWML24	ML 6 3/4"	Particulate Barrier Hood, ML (Case of 10)
PBHWXL24	XL 7 1/4"	Particulate Barrier Hood, XL (Case of 10)




PBH99



Protection Layered in Prevention




Air Permeable



Blocks 99.19% of
particles from 0.1
To 1.0 μm

Exterior Layer: 20% Nomex,
80% Lenzing.



Interior Trilaminate Layer:
PBH99 Materials are
Nomex®, Lenzing, and
Stedair PREVENT® for
on-scene protection.

Bullard Center
2421 Fortune Drive
Lexington, KY 40509 • USA
877-BULLARD (285-5273)
Tel: +1-859-234-6616
Fax: +1-859-246-0243

Americas Operations
1898 Safety Way
Cynthiana, KY 41031 • USA
877-BULLARD (285-5273)
Tel: +1-859-234-6616
Fax: +1-859-234-8987

Bullard GmbH
Dieselstrasse 8a
53424 Remagen • Germany
Tel: +49-2642 999980
Fax: +49-2642 9999829

Bullard Asia-Pacific Pte. Ltd.
LHK Building
701, Simis Drive, #04-03
Singapore 387383
Tel: +65-6745-0556
Fax: +65-6745-5176

©2019 Bullard. All rights reserved.
Nomex is a registered trademark of
E.I. DuPont de Nemours & Company.

(0519)

www.bullard.com